

PEACOCK BORDER

MADE IN JAPAN	GLAZED PORCELAIN
---------------	------------------

PACKAGING

COLOR CODE	SIZE	BOX			PLT		
PB-02/04/05/07/ 09/10/11/14/1506	SHEET SIZE	SH	SQ.FT.	LB(NET WEIGHT)	BOX	SQ.FT.	LB(NET WEIGHT)
	10-3/4"x13" (270x330mm)	20	19.20	48.4	45	864.00	2,178
	PIECE SIZE	SH	SQ.M.	KG(NET WEIGHT)	BOX	SQ.M.	KG(NET WEIGHT)
	1/2"x3-1/2" (12.5x87.5x7mm)	20	1.76	22	45	79.20	990

TEST REPORT

The tiles have been inspected in accordance with JIS (Japanese Industrial Standards) specification.

Test	Result	Specification
Water Absorption	0.124% on average.	JIS A 1509-3 : 2014
Frost Resistance	No deterioration.	JIS A 1509-9 : 2014
Chemical Resistance	As below:	JIS A 1509-10 : 2020
Ammonium chloride solution	No change.	
Hydrochloric acid solution	No change.	
Citric acid solution	No change.	
Potassium hydroxide solution	No change.	
Sodium hypochlorite solution	No change.	

NOTE

Has natural shade variation among batches.

Has size variation within JIS. *JIS: $\pm 0.8\text{mm}$ / $\pm 1.2\text{mm}$ (11.7 ~ 13.3mm / 86.3 ~ 88.7mm)

Clean with neutral detergent.



MARUMAN SHOKAI CO., LTD.

3207-1 Kasahara-cho Tajimi-city Gifu 507-0901 Japan
 TEL: +81-572-43-2201 FAX: +81-572-43-2203
 maruman2@tile-maruman.co.jp <https://tile-maruman.com>