

RIAD

| MADE IN JAPAN | GLAZED PORCELAIN |
|---------------|------------------|
|---------------|------------------|

PACKAGING

| COLOR CODE | SIZE | BOX | | | PLT | | |
|--------------------------------|----------------------------|-----|--------|----------------|-----|--------|----------------|
| | | PC | SQ.FT. | LB(NET WEIGHT) | BOX | SQ.FT. | LB(NET WEIGHT) |
| RD-001/002/003/ 004/005/006 | 2-1/2"x9" (60x227x10mm) | 80 | 12.00 | 55 | 40 | 480.00 | 2,200 |
| | | PC | SQ.M. | KG(NET WEIGHT) | BOX | SQ.M. | KG(NET WEIGHT) |
| | | 80 | 1.08 | 25 | 40 | 43.20 | 1,000 |

*SQ.FT. and SQ.M. quantity is calculated without joint.

TEST REPORT

The tiles have been inspected in accordance with JIS (Japanese Industrial Standards) specification.

| Test | Result | Specification |
|------------------------------|------------------------------------|----------------------|
| Water Absorption | 0.59% on average. | JIS A 1509-3 : 2014 |
| Crazing Resistance | No Crazing. | JIS A 1509-8 : 2014 |
| Frost Resistance | No deterioration. | JIS A 1509-9 : 2014 |
| Bending Fracture Load | 1,810.68N on average | JIS A 1509-4 : 2014 |
| Bending Strength | 47.48 N/mm ² on average | JIS A 1509-4 : 2014 |
| Chemical Resistance | As below: | JIS A 1509-10 : 2014 |
| Ammonium chloride solution | No change. | |
| Hydrochloric acid solution | No change. | |
| Citric acid solution | No change. | |
| Potassium hydroxide solution | No change. | |
| Sodium hypochlorite solution | No change. | |

NOTE

Has natural shade variation among batches.

Has size variation within JIS. *JIS: $\pm 1.2\text{mm}$ / $\pm 2.4\text{mm}$ (58.8 ~ 61.2mm / 224.6 ~ 229.4mm)

May have small pinholes on surface due to its characteristic of pigments.

Clean with neutral detergent.

5mm joint is recommended.



MARUMAN SHOKAI CO., LTD.

3207-1 Kasahara-cho Tajimi-city Gifu 507-0901 Japan
 TEL: +81-572-43-2201 FAX: +81-572-43-2203
 maruman2@tile-maruman.co.jp <https://tile-maruman.com>