## **SAVOR**

| MADE IN JAPAN |            |    |        | GLAZED PORCELAIN |     |        |                |
|---------------|------------|----|--------|------------------|-----|--------|----------------|
| PACKAGING     |            |    |        |                  |     |        |                |
| COLOR CODE    | SIZE       |    | ВО     | X                | PLT |        |                |
|               | SHEET SIZE | SH | SQ.FT. | LB(NET WEIGHT)   | BOX | SQ.FT. | LB(NET WEIGHT) |

| COLOR CODE                     | SIZE                      | вох |        |                | PLT |        |                |
|--------------------------------|---------------------------|-----|--------|----------------|-----|--------|----------------|
| N-100B/201B/<br>202B/205B/206B | SHEET SIZE                | SH  | SQ.FT. | LB(NET WEIGHT) | BOX | SQ.FT. | LB(NET WEIGHT) |
|                                | 12"x12"<br>(303x303mm)    | 22  | 21.78  | 48.4           | 45  | 980.10 | 2,178          |
|                                | PIECE SIZE                | SH  | SQ.M.  | KG(NET WEIGHT) | вох | SQ.M.  | KG(NET WEIGHT) |
|                                | 9/16"x2"<br>(15x47.5x6mm) | 22  | 2.01   | 22             | 45  | 90.45  | 990            |

## **TEST REPORT**

The tiles have been inspected in accordance with JIS (Japanese Industrial Standards) specification.

| Test                                    | Result             | Specification        |  |  |
|---|--------------------|----------------------|--|--|
| Water Absorption                        | 0.126% on average. | JIS A 1509-3 : 2014  |  |  |
| Crazing Resistance                      | No Crazing.        | JIS A 1509-8 : 2014  |  |  |
| Frost Resistance                        | No deterioration.  | JIS A 1509-9 : 2014  |  |  |
| Chemical Resistance                     | As below:          | JIS A 1509-10 : 2020 |  |  |
| Ammonium chloride solution              | No change.         |                      |  |  |
| Hydrochloric acid solution              | No change.         |                      |  |  |
| Citric acid solution                    | No change.         | N2 Y 1203-10 : 5050  |  |  |
| otassium hydroxide solution No change.  |                    |                      |  |  |
| Sodium hypochlorite solution No change. |                    |                      |  |  |

## **NOTE**

Has natural shade variation among batches.

Has size variation within JIS. \*JIS:  $\pm 0.8$ mm (14.2  $\sim 15.8$ mm / 46.7  $\sim 48.3$ mm)

Clean with neutral detergent.