

SEKKA-TOBAN

MADE IN JAPAN	GLAZED PORCELAIN
---------------	------------------

PACKAGING

COLOR CODE	SIZE	BOX			PLT		
		PC	SQ.FT.	LB(NET WEIGHT)	BOX	SQ.FT.	LB(NET WEIGHT)
STB-GR	1-3/4"x8-1/2" (45x215x10mm)	100	11.00	46.2	48	528.00	2,218
		PC	SQ.M.	KG(NET WEIGHT)	BOX	SQ.M.	KG(NET WEIGHT)
		100	0.96	21	48	46.08	1,008

*SQ.FT. and SQ.M. quantity is calculated without joint.

TEST REPORT

The tiles have been inspected in accordance with JIS (Japanese Industrial Standards) specification.

Test	Result	Specification
Water Absorption	0.63% on average.	In-house data in accordance with JIS.
Frost Resistance	No deterioration.	In-house data in accordance with JIS.
Bending Fracture Load	1,257N on average	In-house data in accordance with JIS.
Bending Strength	19N/mm ² on average	In-house data in accordance with JIS.

NOTE

Has natural shade variation among batches.

Has size variation within JIS. *JIS: $\pm 1.5\text{mm}$ / $\pm 3.0\text{mm}$ (43.5 ~ 46.5mm / 212 ~ 218mm)

5mm joint is recommended.



MARUMAN SHOKAI CO., LTD.

3207-1 Kasahara-cho Tajimi-city Gifu 507-0901 Japan
 TEL: +81-572-43-2201 FAX: +81-572-43-2203
 maruman2@tile-maruman.co.jp <https://tile-maruman.com>