

SEKKA-TOBAN

MADE IN JAPAN	GLAZED PORCELAIN
---------------	------------------

PACKAGING

COLOR CODE	SIZE	BOX			PLT		
		PC	SQ.FT.	LB(NET WEIGHT)	BOX	SQ.FT.	LB(NET WEIGHT)
ST-GR	5-1/2"x7-1/2" (140x190x20mm)	22	6.38	55	40	255.20	2,200
		PC	SQ.M.	KG(NET WEIGHT)	BOX	SQ.M.	KG(NET WEIGHT)
		22	0.58	25	40	23.20	1,000

*SQ.FT. and SQ.M. quantity is calculated without joint.

TEST REPORT

The tiles have been inspected in accordance with JIS (Japanese Industrial Standards) specification.

Test	Result	Specification
Water Absorption	0.82% on average.	In-house data in accordance with JIS.
Frost Resistance	No deterioration.	In-house data in accordance with JIS.
Bending Fracture Load	3,866N on average	In-house data in accordance with JIS.
Bending Strength	19N/mm ² on average	In-house data in accordance with JIS.

NOTE

Has natural shade variation among batches.

Has size variation within JIS. *JIS: $\pm 2.5\text{mm}$ / $\pm 3.0\text{mm}$ (137.5 ~ 142.5mm / 187 ~ 193mm)

10mm joint is recommended.



MARUMAN SHOKAI CO., LTD.

3207-1 Kasahara-cho Tajimi-city Gifu 507-0901 Japan
 TEL: +81-572-43-2201 FAX: +81-572-43-2203
maruman2@tile-maruman.co.jp <https://tile-maruman.com>