

## TANTO

| MADE IN JAPAN | GLAZED / UNGLAZED STONEWARE |
|---------------|-----------------------------|
|---------------|-----------------------------|

### PACKAGING

| COLOR CODE           | SIZE                         | BOX       |               |                       | PLT        |               |                       |
|----------------------|------------------------------|-----------|---------------|-----------------------|------------|---------------|-----------------------|
| TNT-1/2<br>TNT-1B/2B | <b>SHEET SIZE</b>            | <b>SH</b> | <b>SQ.FT.</b> | <b>LB(NET WEIGHT)</b> | <b>BOX</b> | <b>SQ.FT.</b> | <b>LB(NET WEIGHT)</b> |
|                      | 10"x10"<br>(252x252mm)       | 20        | 13.80         | 44                    | 45         | 621.00        | 1,980                 |
|                      | <b>PIECE SIZE</b>            | <b>SH</b> | <b>SQ.M.</b>  | <b>KG(NET WEIGHT)</b> | <b>BOX</b> | <b>SQ.M.</b>  | <b>KG(NET WEIGHT)</b> |
|                      | 2-1/2"x2-1/2"<br>(60x60x8mm) | 20        | 1.26          | 20                    | 45         | 56.70         | 900                   |

\*Paper face mounted with 3mm joint.

### TEST REPORT

The tiles have been inspected in accordance with JIS (Japanese Industrial Standards) specification.

| Test                         | Result                  | Specification        |
|------------------------------|-------------------------|----------------------|
| Water Absorption             | 4.37% on average.       | JIS A 1509-3 : 2014  |
| Thermal Shock Resistance     | No deterioration.       | JIS A 1509-7 : 2014  |
| Crazing Resistance           | No Crazing.             | JIS A 1509-8 : 2014  |
| Slip Resistance              | C.S.R. 0.50 on average. | JIS A 1509-12 : 2020 |
| Frost Resistance             | No deterioration.       | JIS A 1509-9 : 2014  |
| Chemical Resistance          | As below:               | JIS A 1509-10 : 2020 |
| Ammonium chloride solution   | No change.              |                      |
| Hydrochloric acid solution   | No change.              |                      |
| Citric acid solution         | No change.              |                      |
| Potassium hydroxide solution | No change.              |                      |
| Sodium hypochlorite solution | No change.              |                      |

### NOTE

Has shade and color variation among batches.

Has size variation within JIS. \*JIS:  $\pm 1.2\text{mm}$  (58.8 ~ 61.2mm)

Clean with neutral detergent.

Joint filler material remains in the hollows. Filler is also prone to remaining in unglazed check-pattern areas, and so black filler should be avoided.

Some areas of the sides are bare of glaze, but this is a characteristic of the manufacturing process and not a defect.



**MARUMAN SHOKAI CO., LTD.**

3207-1 Kasahara-cho Tajimi-city Gifu 507-0901 Japan

TEL: +81-572-43-2201

FAX: +81-572-43-2203

maruman2@tile-maruman.co.jp

<https://tile-maruman.com>