WINDOWPANE

	MADE IN JAPAN	1	GLAZED PORCELAIN					
PACKAGING PACKAGING								
COLOR CODE	SI7F	вох	PLT					

COLOR CODE	SIZE	вох			PLT		
		PC	SQ.FT.	LB(NET WEIGHT)	BOX	SQ.FT.	LB(NET WEIGHT)
WP-1/2/3/4	4"x8" (97x197x8mm)	40	8.40	33	56	470.40	1,848
		PC	SQ.M.	KG(NET WEIGHT)	вох	SQ.M.	KG(NET WEIGHT)
		40	0.76	15	56	42.56	840

^{*}SQ.FT. and SQ.M. quantity is calculated without joint.

TEST REPORT

The tiles have been inspected in accordance with JIS (Japanese Industrial Standards) specification.

Test	Result	Specification		
Water Absorption	0.212% on average.	JIS A 1509-3 : 2014		
Crazing Resistance	No Crazing.	JIS A 1509-8 : 2014		
Frost Resistance	No deterioration.	JIS A 1509-9 : 2014		
Chemical Resistance	mical Resistance As below:			
nmonium chloride solution No change.				
Hydrochloric acid solution	No change.	JIS A 1509-10 : 2014		
Citric acid solution	No change.	JIS A 1509-10 : 2014		
Potassium hydroxide solution	No change.			
dium hypochlorite solution No change.				

NOTE

Has natural shade variation among batches.

Has size variation within JIS. *JIS: ± 1.2 mm / ± 2.4 mm (95.8 ~ 98.2 mm / 194.6 ~ 199.4 mm)

Clean with neutral detergent.

3mm joint is recommended.