

## CLAY MASTER

**MADE IN JAPAN**

**UNGLAZED PORCELAIN**

### PACKAGING

COLOR CODES	UNIT	SIZE	BOX			PALLET		
			PC	SQ.FT.	LB(NET WEIGHT)	BOX	SQ.FT.	LB(NET WEIGHT)
CM-A/B/C/D	INCH/FEET	5-1/2"x7-1/2"	29	8.41	52.8	40	336.40	2,112
	METRIC	140x190x15mm	29	0.77	24	40	30.80	960

\*SQ.FT. and SQ.M. quantity is calculated without joint.

### TEST REPORT

The tiles have been inspected in accordance with JIS (Japanese Industrial Standards) specification.

Test	Result	Specification
Water Absorption	0.47% on average.	In-house data in accordance with JIS.
Frost Resistance	No deterioration.	In-house data in accordance with JIS.
Bending Fracture Load	3,861N on average	In-house data in accordance with JIS.
Bending Strength	26 N/mm <sup>2</sup> on average	In-house data in accordance with JIS.

### NOTE

Has natural shade variation among batches.

Has size variation within JIS. \*JIS:  $\pm 2.5\text{mm} / \pm 3.0\text{mm}$ (137.5~142.5mm / 187.0~193.0mm)

10mm joint is recommended.

As this product has not yet been tested, the above data has been provisionally entered using the same material and dimensions as MATSUBAI-TOBAN (140x190x15mm). This product will be tested at a later date.



**MARUMAN SHOKAI CO., LTD.**

3207-1 Kasahara-cho Tajimi-city Gifu 507-0901 Japan  
 TEL: +81-572-43-2201 FAX: +81-572-43-2203  
 maruman2@tile-maruman.co.jp <https://tile-maruman.com>