

CLAY MASTER LIGHT

MADE IN JAPAN

UNGLAZED PORCELAIN

PACKAGING

COLOR CODES	UNIT	SIZE	BOX			PALLET		
			PC	SQ.FT.	LB(NET WEIGHT)	BOX	SQ.FT.	LB(NET WEIGHT)
CMLQ-A/B/C/D/E	INCH/FEET	1-1/8"x8"	174	12.18	50.6	40	487.20	2,024
	METRIC	30x200x10.5mm	174	1.04	23	40	41.60	920

*SQ.FT. and SQ.M. quantity is calculated without joint.

TEST REPORT

The tiles have been inspected in accordance with JIS (Japanese Industrial Standards) specification.

Test	Result	Specification
Water Absorption	0.44% on average.	In-house data in accordance with JIS.
Bending Fracture Load	308N on average	In-house data in accordance with JIS.
Bending Strength	27N/mm ² on average	In-house data in accordance with JIS.
Chemical Resistance	As below:	JIS A 1509-10 : 2020
Ammonium chloride solution	No change.	
Hydrochloric acid solution	No change.	
Citric acid solution	No change.	
Potassium hydroxide solution	No change.	
Sodium hypochlorite solution	No change.	

NOTE

Has natural shade variation among batches.

Has size variation within JIS. *JIS: ± 1.5mm/3.0mm (28.5~31.5 x 197~203mm)

5mm joint is recommended.



MARUMAN SHOKAI CO., LTD.

3207-1 Kasahara-cho Tajimi-city Gifu 507-0901 Japan
 TEL: +81-572-43-2201 FAX: +81-572-43-2203
 maruman2@tile-maruman.co.jp <https://tile-maruman.com>