

TANTO

MADE IN JAPAN
GLAZED / UNGLAZED STONEWARE

PACKAGING

COLOR CODES	UNIT	SIZE		BOX			PALLET		
		PIECE SIZE	SHEET SIZE	SH	SQ.FT.	LB(NET WEIGHT)	BOX	SQ.FT.	LB(NET WEIGHT)
TNT-1/2 TNT-1B/2B	INCH/FEET	2-1/2"x2-1/2"	10"x10"	20	13.80	44	45	621.00	1,980
	METRIC	PIECE SIZE	SHEET SIZE	SH	SQ.M.	KG(NET WEIGHT)	BOX	SQ.M.	KG(NET WEIGHT)
		60x60x8mm	252x252mm	20	1.26	20	45	56.70	900

*Paper face mounted with 3mm joint.

TEST REPORT

The tiles have been inspected in accordance with JIS (Japanese Industrial Standards) specification.

Test	Result	Specification
Water Absorption	4.37% on average.	JIS A 1509-3 : 2014
Thermal Shock Resistance	No deterioration.	JIS A 1509-7 : 2014
Crazing Resistance	No Crazing.	JIS A 1509-8 : 2014
Slip Resistance	C.S.R. 0.50 on average.	JIS A 1509-12 : 2020
Frost Resistance	No deterioration.	JIS A 1509-9 : 2014
Chemical Resistance	As below:	JIS A 1509-10 : 2020
Ammonium chloride solution	No change.	
Hydrochloric acid solution	No change.	
Citric acid solution	No change.	
Potassium hydroxide solution	No change.	
Sodium hypochlorite solution	No change.	

NOTE

Has shade and color variation among batches.

Has size variation within JIS. *JIS: $\pm 1.2\text{mm}$ (58.8 ~ 61.2mm)

Clean with neutral detergent.

Joint filler material remains in the hollows. Filler is also prone to remaining in unglazed check-pattern areas, and so black filler should be avoided.

Some areas of the sides are bare of glaze, but this is a characteristic of the manufacturing process and not a defect.


MARUMAN SHOKAI CO., LTD.

3207-1 Kasahara-cho Tajimi-city Gifu 507-0901 Japan
 TEL: +81-572-43-2201 FAX: +81-572-43-2203
 maruman2@tile-maruman.co.jp <https://tile-maruman.com>